

Significance of Waste Materials in Sustainable Concrete and Sustainable Development

M. R. Karim ¹, M. F. M. Zain ¹, M. Jamil ¹, F.C. Lai ²

¹ Universiti Kebangsaan Malaysia, Malaysia.

² Regional Technology Support Centre, Sika Kimia Sdn Bhd, Malaysia

Abstract. In this paper, a critical review on the significance and consumption of waste materials - slag, rice husk ash (RHA), palm oil fuel ash (POFA), fly ash (FA) - as a supplement of cement and ingredient of concrete for the production of sustainable concrete as well as sustainable development has been presented. The benefits of supplementary use of waste materials in cement and concrete have also been listed here. However, based on the information from published literatures, it is concluded that proper utilization of waste materials as a substitute of cement and constituent of concrete will be a valuable and effective way for production of sustainable concrete as well as sustainable development for comfortable and continued existence of present and future generation in the planet.

Keywords: waste materials (slag, FA, RHA, POFA), sustainable concrete, energy, CO₂ emission

1. Introduction

It is well known that sustainable development, one of the most important issues in the world at present days, involves to build our communities in such a way that we can all live comfortably without consuming all of our resources, we make an impact on the environment through how we survive our lives. To fulfil the basic needs of human life, demands are increasing gradually including clean water, clean air, waste disposal, safe and rapid transport of people and goods, residential and industrial buildings, and sources of energy. In fact, it is well accepted by everyone that concrete executes outstanding responsibilities for the construction of modern infrastructures, industrialization and urbanization for the growing population in the globe. Besides, it is relevant to mention that the concrete industry today is the largest consumer of natural resources - water, sand, gravel, and crushed rock. For these reasons, sustainable concrete is one of the prime topics in concrete industry all over the world and its main objectives are: reduction the amount of polluting and carbon dioxide (CO₂) gases emitted during the manufacture of concrete; more efficient use of waste materials; development of a low-energy, long-lasting, flexible buildings and structures; exploiting the thermal mass of concrete in a structure to reduce energy demand. Nowadays, ordinary Portland cement (OPC), the second most consumed material after water, is used as a key ingredient in concrete production for modern infrastructural needs. Not surprisingly, about 7% world's CO₂ is released to atmosphere due to OPC manufacturing alone [1]; in consequence, global warming is rising day by day. The burning of OPC clinker (around 1400⁰C) is not only liable for CO₂ emissions but also it is costly in terms of fossil fuel usage. Overall, a special responsibility and alternative way would be executed by researchers, engineers and all concerns of concrete technology for solving these. Thus, all of these problems, particularly in concrete sector, could be solved/minimized simultaneously by proper utilization of waste materials (slag, RHA, POFA, FA, ash from timber, silica fume, etc.) as an ingredient of cement or constituent of concrete that are suggested by several researchers. Thus, the significance and necessity of consumption of these waste materials for the manufacturing of sustainable concrete as well as sustainable development have been highlighted in this paper.

2. Production and Consumption of Wastes

Nowadays, the demands and consumptions of goods from every sector (e.g. industrial, agricultural) are increasing due to the increasing population whole over the world. As a results, huge quantity of various types of wastes are also been generated from those sectors as a by-products. Among the different types of waste in the world, only the author’s interested waste (slag, RHA, POFA, FA, silica fume) generation view is presented in Table1. Slag is a by-product from still mills; fly ash (FA), the waste generated from coal operated power plant, silica fume is mainly generated from silicon industries; rice husk is the outer covering of paddy, generated from rice mills; POFA is produced from the palm oil fuel mills. These waste generation trends are increasing gradually due to the increasing demand in various industrial and agricultural sectors. Owing the technical advantages of RHA, unfortunately, only a little fraction of these RHA are being used for different purpose such as heat producing in the rice processing mills as alternative of fuel but most of them are dumped as garbage. Although, a few quantities of rice husks are being used as animal’s and fish food. As seen from Table 1, there is no exact statistics of consumption of these wastes, only a small portion of these wastes is consumed for different purposes. Although these waste bears valuable and technical merits, but these are simply dumped into ponds, lagoons or as disposed as landfills. However, all of these waste are contain high percent of silica; consequently, more suggestions have been come out from various researchers to use these as supplement of cement of as ingredient of concrete. How their contribution enhanced the properties of concrete as well as in sustainable concrete that is explained in following section.

Table1: Production and consumption of various wastes

| Name of wastes | Production source | Quantity (million ton) | Consumption (million ton) | Reference |
|----------------|---------------------------|--|---------------------------|-----------|
| Slag | Steel industries | 100.00 | 35 | [2] |
| FA | Coal operated power plant | 900.00 | * | [3] |
| POFA | Palm oil mills | More than thousand ton | * | [4] |
| Rice husk | Rice processing mills | 110.00 (@ 20% from 550 million ton rice) | * | [5] |
| RHA | | 16.50 to 22.00 | * | |
| Silica fume | Silicon industries | 2.00 | * | [3] |

*Few portion (not exactly specified)

3. Benefits of Waste Materials as Cement Replacement

Waste materials when processed properly could be used as valuable engineering materials and could also be satisfy the design requirements. In this connection, the following examples are pointed out. For producing high-strength concrete, POFA can be used as a pozzolanic material; it improves the durability and reduces cost due to less use of cement. It will also be beneficial for the environment with respect to reducing the waste disposal volume of landfills. POFA contains the silica oxide that can react with calcium hydroxide ($\text{Ca}(\text{OH})_2$) generated from the hydration process; and the pozzolanic reactions produce more secondary calcium silicate hydrate (C-S-H) gel compound as well as reducing the amount of calcium hydroxide. Thus, for the concrete production, POFA contributes to make stronger, denser and more durable concrete. POFA, RHA and fly ash (FA) can be used as pozzolans to replace part of Portland cement in making mortar with relatively high strength and good resistance to chloride penetration [6]. These wastes are abundantly available in Malaysia and have been proved as pozzolanic materials [7]. Ground POFA with high fineness can be used as a cement replacement to produce high-strength concrete with a compressive strength as high as 70 MPa at 90 days when used to replace Type I Portland cement at 20% by weight of binder [8]. Hale et al. [9] found that replacements rates of 15% for fly ash and 25% for slag cement improved long term concrete properties without much sacrifice in early age properties. RHA has been used in lime pozzolana mixes and could be a suitable partly replacement for Portland cement [10-12]. Ground POFA is a good pozzolanic material and can be used to increase both the compressive strength and the sulfate resistance of mortar [13]. Pozzolans from industrial and agricultural by-products such as FA and RHA are receiving more attention now since their uses generally improve the properties of the blended cement concrete, and reduce the cost

and negative environmental effects [14]. The 28-day compressive strengths of the saw dust ash (timber ash)/OPC concretes at 5%, 10% and 15% of levels of replacement of cement are about 93%, 78% and 68% of the control mix, respectively [15]. Haque [16] suggested that the proper use of the fine FA can produce both high strength and high performance concrete. Quaternary blended cement (RPTS cement) with replacement of OPC up to 66% can be used for the production of high strength (100 MPa-120 MPa) sustainable high performance concrete [17]. Slag is commonly used in concrete because it improves durability and reduces porosity; improve the interface with the aggregate; lower cement requirement; save energy; and good performance as well as better engineering properties [18]. In addition, several other advantages of these wastes have been given below:

- RHA can be incorporated either as an admixture or as cement replacement material [19].
- Slags have been used as aggregates for road construction, about 97% of the produced steel slag have used during construction of surface layer, road base and sub base for high tracked roads in Germany in 1998 [20].
- With high fineness, POFA can be used as a cement replacement to produce high-strength concrete; it also reduces the water permeability of concrete [8].
- POFA can be used as a cement replacement to produce good resistance against sulfate attack [21-22].
- RHA Improves compressive strength [23-25], flexural strengths of concrete [26-27]; and split tensile strength of concrete [28-30].
- RHA mixed concrete shows better bond strength compare to OPC concrete [25]; [29].

4. Necessity and Possible Ways of Sustainable Construction

As we know, cement and concrete industries is the third energy consumer after aluminium and steel [2]. Besides, huge amount of natural stones, sand, and water is being consuming by the concrete construction. It could be noted that about 850 to 900 kcal/kg (in the dry process), and 1300-1600 kcal/kg (in the wet process) heat energy is required in cement production [31]. However, the global average electricity consumption is approximately 111 kWh per ton of cement production [32]. The embodied energy requirement is nearly 817,600 BTU per ton of concrete production, from which maximum (94%) is comes from cement manufacturing [33]. As a result, natural resources and energies (fuel or electrical) are depleting gradually. Thus, it is great warning for us as well as the future generation for the preservation of the natural resources and energies. Therefore, it is the optimum time to find an alternative way of concrete production or to search another sustainable binder that can be used as supplement of cement for the sustainable concrete production; more amounts of wastes consumption in cement and concrete manufacturing could be another solution. Because, consumption of wastes in cement and concrete production could be reduced the energy demand as well as reduced the CO₂ emission rate. For example, 1587kWh/ton energy is required for CEM I (without slag), but the requirement is 1206 kWh/ton, 938 kWh/ton and 602 kWh/ton for the addition of 30%, 50% and 75% slag respectively [34]. Besides, 300 million tons of CO₂ could be reduced by replacing only 18.5% of the cement with slag or fly ash per year in the world [35]. Furthermore, we all the concerns in concrete construction have the responsibilities to preserve our natural resources and prevent the CO₂ emission by utilizing more wastes in cement and concrete manufacturing to achieve the sustainable concrete as well as sustainable development. In addition, awareness regarding sustainable construction and sustainable development could spread out among the designer, developer, proprietor and the general public in the society.

5. Concluding Remarks

In fact, to survive in the global community, production would be continued from various sectors, consequently, waste must be generated from those sectors as well. Thus, searching a sustainable as well as less energy demanded production technology from different sectors, including cement and concrete construction, could be investigated. Additionally, waste consumption policy could also be applied in large scale as a part of sustainable concrete construction. The goal of sustainable construction and sustainable development could be achieved by consuming wastes in cement and as an ingredient of concrete as prescribed by several researchers, because, incorporation of wastes in cement and concrete not only reduce the CO₂ emission but also improve the strength and durability properties of concrete; production cost of

concrete would also been reduced. Furthermore, proper utilization and consumption of waste is valid, logical and significant issue to reach the sustainable world for the future inhabitants.

6. Acknowledgements

The authors would be grateful to Allah Almighty. Universiti Kebangsaan Malaysia; Ministry of Science, Technology and Innovation; Fundamental Research Grant Scheme (FRGS); and Department of Civil and Structural Engineering are highly appreciated for financial supporting of the research.

7. References

- [1] P. K. Mehta. Concrete technology for sustainable development. *Concr. Int.* 1999, 21(11): 47 - 53.
- [2] M. Nehdi. Ternary and quarternary cements for sustainable development. *Concr. Int.* 2001:35-42
- [3] V. M. Malhotra. Reducing CO₂ emissions. *ACI Concr. Int.* 2006, 28(9):42-45.
- [4] A. S. M. A Awal, and M.W. Hussin. The effectiveness of palm oil fuel ash in preventing expansion due to alkali-silica reaction. *Cem. Concr. Compos.* 1997, 19(4): 367-372
- [5] Torbed. Energy Technology Application Description, Energy & Amorphous Silica Production From Rice Husk, Accessed on April 15, 2011. Available In:
<http://www.torftech.com/pdf/application%20description%20-%20rice%20hulls.pdf>
- [6] P. Chindapasirt, S. Rukzon and V. Sirivivatnanon. Resistance to chloride penetration of blended Portland cement mortar containing palm oil fuel ash, rice husk ash and fly ash. *Constr. Build. Mater.* 2008, 22: 932-938.
- [7] E. I. Mohamed, M.W. Hussin, and M. Ismail. High performance blended cement concrete in Malaysia, Paper presented at 8th International Symposium on utilization of high-strength and high-performance concrete .2008, Tokyo, Japan.
- [8] W. Tangchirapat, C. Jaturapitakkul, and P. Chindapasirt. Use of palm oil fuel ash as a supplementary cementitious material for producing high-strength concrete. *Constr. Build. Mater.* 2009, 23(7): 2641-2646.
- [9] W. M. Hale, S. F. Freyne, T. D. Bush Jr., and B. W. Russell. Properties of concrete mixtures containing slag cement and fly ash for use in transportation structures. *Constr. Build. Mater.* 2008, 22:1990–2000.
- [10] V. Sata, C. Jaturapitakkul, and K. Kiattikomol. Influence of pozzolan from various by-product materials on mechanical properties of high-strength concrete. *Constr. Build. Mater.* 2007, 21(7): 1589–1598.
- [11] P. H. Nicole, P. J. M. Monteiro, and H. Carasek. Effect of silica fume and rice husk ash on alkali-silica reaction. *Mater. J.* 2000, 97(4): 486-492.
- [12] M. H. Zhang and V. M. Malhotra. High-performance concrete incorporating rice husk ash as a supplementary cementing material. *ACI Mater. J.* 1996, 93 (6): 629–636.
- [13] W. Tangchirapat, C. Jaturapitakkul, and K. Kiattikomol. Compressive strength and expansion of blended cement mortar containing palm oil fuel ash. *J. Mater. Civil Engg.* 2009, 21(8): 426-431.
- [14] P. Chindapasirt, and S. Rukzon. Strength, porosity and corrosion resistance of ternary blend Portland cement, rice husk ash and fly ash mortar. *Constr. Build. Mater.* 2008, 22: 1601–1606.
- [15] A. C. Elinwa, and Y. A. Mahmood. Ash from timber waste as cement replacement material. *Cem. Concr. Compos.* 2002, 24:219–222.
- [16] M. N. Haque, and O. Kayali. Properties of high-strength concrete using a fine fly ash. *Cem. Concr. Res.* 1998, 28 (10): 1445–1452.
- [17] F. C. Lai. High volume quaternary blended cement for sustainable high performance concrete. Paper presented at 34th Conference on Our World in Concrete & Structures: 16-18 August 2009, Singapore, pp. 175-180.
- [18] H. B. Mahmud, E. Majuar, M. F. M. Zain, and N. B. A. A. Hamid. Mechanical properties and durability of high strength concrete containing rice husk ash. *J. Adv. Concr. Tec.* 2009, 79: 21-30.
- [19] A. Oner, and S. Akyuz. An experimental study on optimum usage of GGBS for the compressive strength of concrete. *Cem. Concr. Compos.* 2007, 29: 505–514.

- [20] H. Motz, and J. Geiseler. Products of steel slags an opportunity to save natural resources. *Waste Manage.* 2001, 21: 285-293.
- [21] C. Jaturapitakkul, K. Kiattikomol, W. Tangchirapat, and T. Saeting. Evaluation of the sulfate resistance of concrete containing palm oil fuel ash. *Constr. Build. Mater.* 2007, 21 (7): 1399-1405.
- [22] W. Tangchirapat, T. Saeting, C. Jaturapitakkul, K. Kiattikomol, and A. Siripanichgorn. Use of waste ash from palm oil industry in concrete. *Waste Manage.* 2007, 27: 81-88.
- [23] N.A. Givi, S.A Rashid, F. N. A Aziz, and S. M. A. Mohd. Assessment of the effects of rice husk ash particle size on strength, water permeability and workability of binary blended concrete. *Constr. Build. Mater.* 2010, 24: 2145–2150.
- [24] M. Safiuddin, J. S. West, and K. A. Soudki. Hardened properties of self-consolidating high performance concrete including rice husk ash. *Cem. Concr. Compos.* 2010, 32: 708–717.
- [25] V. Saraswathy, and S. Ha-Won. Corrosion performance of rice husk ash blended concrete. *Constr. Build. Mater.* 2007, 21 (8): 1779–1784.
- [26] J. S. Coutinho. The combined benefits of CPF and RHA in improving the durability of concrete structures. *Cem. Concr, Compos.* 2003, 25(1): 51-59.
- [27] M. H. Zhang, R. Lastra, and V. M. Malhotra. Rice husk ash paste and concrete: Some aspects of hydration and the microstructure of the interfacial zone between the aggregate and paste. *Cem. Concr. Res.* 1996, 26 (6): 963-977.
- [28] G. A. Habeeb, and M. M. Fayyadh. Rice husk ash concrete: the effect of RHA average particle size on mechanical properties and drying shrinkage. *Aus. J. Bas. App. Sci.* 2009, 3(3):1616-1622.
- [29] K. Sakr. Effects of silica fume and rice husk ash on the properties of heavy weight concrete. *J. Mater. Civil Engg.* 2006, 18 (3): 367-376.
- [30] G. R. De Sensale. Strength development of concrete with rice-husk ash. *Cem. Concr. Compos.* 2006, 28(2): 158-160.
- [31] *Climate Policy Assessment for India*, University Press, 2004
- [32] IEA. 2007, Tracking Industrial Efficiency and CO₂ Emissions, 4a. Energy Technology Transitions for Industry, Strategies for the Next Industrial Revolution, IEA, 2009.
- [33] A. Wilson. Cement and concrete: environmental considerations. Accessed on April 12, 2011. Available in BuildingGreen.com: <http://www.buildinggreen.com/features/cem/cementconc.cfm>
- [34] A. Ehrenberg, and Geiseler, *Jokologische Eigenschaften von Hochofenzement*, Bstn-Informationen, 37(4): 51-63, In: Bensted and Barnes, *Structure and Performance of Cement*, Second Edition, Spon press London and New York, 1997, pp.310-325.
- [35] T. W. Bremner. Invited Paper for the Plenary Session of the 1st All-Russian Conference on Concrete and Reinforced Concrete, 9-14 September, 2001. Accessed on June 23, 2011, Available on: <http://www.unb.ca/civil/materials/materialsgrp/eac.pdf>